



## RCxx30 WAXY TOPCOAT

### FIELD OF APPLICATION

Doors and windows, garden furniture, claddings, balconies, enclosures, matchboardings, beams.

### INFORMATION

This coating is soft to the touch. It makes the wood water-repellent, resistant and durable. It enhances the natural matt aspect. This product protects the wood from atmospheric agents and UV light, excepted the transparent version, because it is iron oxide free. 5-10% dilution with water is possible to improve the application of the product.

### INSTRUCTIONS

*Stained/impregnated wood.* It is possible to apply RCxx30 on wood treated with low-solid content dyes or wood stains. Once the surface has been cleaned, sand with sandpaper or scotch brite. Then remove the powder and apply 1-2 coats of product.

*Coated wood.* On a paint finish which is in good condition, it is necessary to sand with 320 grit sandpaper. Clean the surface, then proceed to paint. On a paint finish which is in bad condition, sand with 80-150 grit sandpaper to bring the wood back to the raw condition. Clean the surface and proceed to paint. Application of 1-2 coats of Wood Stain RMxx10 or Gel Wood Stain RGxx80 before RCxx30 is recommended.

### MAINTENANCE

In case of objects, which are very exposed to the atmospheric agents, it is sufficient to treat only the parts that begin to deteriorate. Slightly sand the object with 220-320 grit sandpaper, remove the powder and apply one coat of the desired colour. On the most deteriorated parts it is possible to apply a second coat. If the object is not much exposed to the atmospheric agents, the maintenance operations will be less frequent. To extend the protective action of the film and the aspect of the object it is recommended to clean with Neutral Detergent T.Clean RR1050 and Brightener T.Top+ RR1250 every six months. Avoid aggressive detergents.

### OVERCOATING

Waxy Topcoats RCxx30 range.

### PACKAGING

0,75 L

2,5 L

5 L

25 L



Storage  
> 5°C



Painting  
> 10°C



Ready to use



Brush  
Spray gun



Yield  
10 m<sup>2</sup>/L



Mix it well  
before use



Drying time  
between the coats  
2-6 h



Final drying time  
12 h



Solid content  
32 ± 3 %



Viscosity  
DIN8 14 ± 3"



Specific weight  
1,05 ± 0,1 g/cm<sup>3</sup>



pH  
8,5 ± 1,0



Gloss level  
12



**RC2030**  
TRANSPARENT



**RC3030**  
HONEY

\*Except for the transparent version