

# FIELD OF APPLICATION

Doors and windows, garden furniture, claddings, balconies, enclosures, matchboardings, beams.

### INFORMATION

It makes the wood water-repellent, resistant and durable. Do not use on white wood stains, on which the completely colourless Waxy Topcoat RC2030 is recommended. 5-10% dilution with water is possible to improve the application of the product.

#### **INSTRUCTIONS**

Stained/impregnated wood. It is possible to apply RFxx20 on a wood treated with low-solid content dyes or wood stains. Once the surface has been cleaned, sand with sandpaper or scotch brite. Then remove the powder and apply 1-2 coats of product. Coated wood. On a paint finish which is in good condition, it is necessary to sand with 320 grit sandpaper. Clean the surface, then proceed to paint. On a paint finish which is in bad condition, sand with 80-150 grit sandpaper to bring the wood back to the raw condition. Clean the surface and proceed to paint. Application of 1-2 coats of Wood Stain RMxx10 or Gel Wood Stain RGxx80 before RFxx20 is recommended.

### **MAINTENANCE**

In case of objects, which are very exposed to the atmospheric agents, it is sufficient to treat only the parts that begin to deteriorate. Slightly sand the object with 220-320 grit sandpaper, remove the powder and apply one coat. On the most deteriorated parts it is possible to apply a second coat. If the object is not much exposed to the atmospheric agents, the maintenance operations will be less frequent. To extend the protective action of the film and the aspect of the woodwork it is recommended to clean with Neutral Detergent T.Clean RR1050 and Brightener T.Top+ RR1250 every six months. Avoid aggressive detergents.

## **OVERCOATING**

Classic Topcoat RFxx20, UV Defender Topcoat RQxx70 and Waxy Topcoat RCxx30.

### **PACKAGING**

0,75 L

2,5 L

10 L











Storage > 5°C



Painting > 10°C



Ready to use



Brush Spray gun



Yield 10 m²/L



Mix it well before use



Drying time between the coats 2-6 h



Final drying time 12 h



Solid content  $35 \pm 3 \%$ 



Viscosity DIN8 14 ± 3"



Specific weight  $1,05 \pm 0,1 \text{ g/cm}^3$ 



pH  $8,5 \pm 1,0$ 



Gloss level 30 for RF1020 60 for RF1120



