



RP1060 GRAIN FILLER

FIELD OF APPLICATION

Wood floorings and furniture.

INFORMATION

It is a transparent primer to be applied on wood floorings and furniture. It is formulated with acrylic-polyurethane resins, it is elastic and can be easily sanded.

INSTRUCTIONS

Sand the raw wood with 150 grit sandpaper and remove the powder with vacuum-cleaner. Apply 1-2 coats of RP1060 at an interval of 2-4 hours. Do not sand between the two coats. Wait for 24 hours before proceeding with the next sanding step, then apply Floorings and furniture topcoat RP1160 or RP2260.

OVERCOATING

Floorings and furniture topcoats RPxx60.

PACKAGING

0,75 L

2,5 L

-  Storage > 5°C
-  Painting > 10°C
-  Ready to use
-  Brush
Spray gun
Roller
-  Yield 10 m²/L
-  Mix it well before use
-  Drying time between the coats 2-4 h
-  Final drying time 24 h
-  Solid content 33 ± 3 %
-  Viscosity DIN4 17 ± 3"
-  Specific weight 1,03 ± 0,1 g/cm³
-  pH 8,0 ± 1,0

